

HTF Curve

Temperature DEG C	SLFI DE-32	SLFI DE-20
	Kinematic Viscosity (cSt)	Kinematic Viscosity (cSt)
-40	19283.44	16315.39
-35	9945.32	7500.39
-30	5429.06	3722.03
-25	3118.41	1976.13
-20	1874.94	1113.86
-15	1174.60	662.07
-10	763.63	412.54
-5	513.33	268.09
0	355.66	180.87

5	253.26	126.18
10	184.88	90.70
15	138.04	66.97
20	105.20	50.66
25	81.68	39.15
30	64.51	30.85
35	51.75	24.74
40	42.10	20.16
45	34.70	16.66
50	28.94	13.95
55	24.40	11.82
60	20.79	10.12
65	17.87	8.74

70	15.49	7.63
----	-------	------

75	13.53	6.70
----	-------	------

80	11.91	5.94
----	-------	------

85	10.55	5.29
----	-------	------

90	9.41	4.75
----	------	------

95	8.43	4.29
----	------	------

100	7.60	3.89
-----	------	------

105	6.88	3.55
-----	------	------

110	6.26	3.25
-----	------	------

115	5.72	2.99
-----	------	------

120	5.25	2.76
-----	------	------

125	4.84	2.56
-----	------	------

130	4.47	2.38
-----	------	------

135	4.15	2.22
-----	------	------

140	3.86	2.08
-----	------	------

145	3.60	1.95
-----	------	------

150	3.36	1.83
-----	------	------

155	3.15	1.73
-----	------	------

160	2.97	1.63
-----	------	------

165	2.79	1.55
-----	------	------

170	2.64	1.47
-----	------	------

175	2.50	1.40
-----	------	------

180	2.37	1.33
-----	------	------

185	2.25	1.27
-----	------	------

190	2.14	1.22
-----	------	------

195	2.04	1.17
-----	------	------

200	1.95	1.12
205	1.86	1.08
210	1.78	1.04
215	1.71	1.00
220	1.64	0.96
225	1.57	0.93
230	1.52	0.90
235	1.46	0.87
240	1.41	0.84
245	1.36	0.82
250	1.31	0.80
255	1.27	0.77
260	1.23	0.75
